

## CLAIMS:

1. A method of manufacturing composite products, wherein a plurality of elements are assembled by gluing them together under pressure, comprising the steps of:

providing a number of elements to be assembled;

applying glue to at least one surface of each element;

assembling the elements to the desired structure; and

subjecting the assembled elements to pressure in a press;

controlling the amount of at least one component of the glue, applied at a specific point of glue application on an element, to be a function of the waiting time it takes before the point of glue application is subjected to the pressure in the press.

2. The method according to claim 1, wherein the glue is a multi-component adhesive, one component of which is a hardener and wherein the amount of one of said adhesive components is controlled so as to control the ratio between hardener and remaining components to be a function of the waiting time.

3. The method according to claim 2, wherein the glue is a two-component adhesive comprising hardener and a glue, the ratio hardener:glue is controlled to be lower for longer waiting times.

4. The method according to claim 1, wherein the glue is a one-component glue, and the amount of is increased as a function of increased waiting time.

5. The method according to claim 4 wherein the amount of glue applied to each element is constant over the surface of said element, but varies between elements.

6. The method according to claim 4, wherein the first element in a series of elements receives a smaller amount of glue than subsequent elements.

Sub A11  
09/07/2000

Sub A2

~~The method at  
controlling the speed~~

10

06/10/2016 - 12:10

15

20

25

Sub A3

30

a press (17);

5 ~~5~~ said control unit (15) being programmable to run a control sequence for the glue applicator (10) and/or the element feeder (6; 16) to provide an optimal applied glue amount.

15. The apparatus as claimed in claim 12, wherein the control sequence is adapted to control the speed of movement of the feeder (6; 16), and thereby of the elements through the glue applicator (10).

16. The apparatus as claimed in claim 14, wherein the control sequence is adapted to control the rate of glue application to the elements.

10 17. An apparatus for the controlled application of glue to elements to be assembled to a composite structure, comprising

15 an element feeder (6; 16);

a glue applicator (10); and

a control unit (15);

20 said control unit (15) being programmable to run a control sequence for the glue applicator (10) and/or the element feeder (6; 16) to provide an optimal applied glue amount.